



CHEMLOK[®]
Adhesives

When it's critical,
it's Chemlok.

CHEMLOK 6100

LORD Chemlok[®] 6100 adhesive is a covercoat adhesive that bonds a variety of elastomers to various metals. It is composed of a mixture of polymers, organic compounds and mineral fillers dissolved or dispersed in an organic solvent system.

Chemlok 6100 adhesive provides excellent adhesion to mechanically or chemically treated cold rolled steel or aluminum and is highly resistant to salt spray.

ADVANTAGES

Versatile – Bonds a variety of elastomers and metals when used in combination with Chemlok 205 or 207 primer.

Easy to Apply – Applies easily by spray, dip or brush methods.

Excellent Appearance – Provides a continuous film appearance.

Process Compatible – Resists sweeping; accommodates a wide range of processing conditions including extended prebake.

Environmentally Resistant – Provides excellent resistance to salt spray.

Convenient – Requires only a single coat for most applications, reducing labor, solvent usage, inventory and shipping costs.

PRODUCT INFORMATION*

Appearance	Black Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 2, 30 rpm	350–750
Density kg/m ³ (lb/gal)	940.0–980.0 (7.8–8.2)
Solid Content by Weight, %	21–24
Flash Point (Seta), °C (°F)	27 (81)
Solvents	Xylene

*Data is typical and not to be used for specification purposes.

ELASTOMERS

- Natural Rubber (NR)
- Polyisoprene (IR)
- Styrene-butadiene (SBR)
- Polybutadiene (BR)
- Polychloroprene (CR)
- Nitrile (NBR)
- Butyl (IIR)
- EPDM Polymers

LORD

APPLICATION

Surface Preparation

Thoroughly clean metal surfaces prior to adhesive application. Remove protective oils, cutting oils and greases by solvent degreasing or alkaline cleaning. Remove rust, scale or oxide coatings by suitable chemical or mechanical cleaning methods.

Allow primer to thoroughly dry before applying Chemlok 6100 adhesive.

For further detailed information on surface preparation of specific substrates, refer to Chemlok Adhesives application guide.

Mixing

Thoroughly stir adhesive before use, and agitate sufficiently during use to keep dispersed solids uniformly suspended. If dilution is needed, use xylene or toluene.

Applying

Apply adhesive by brush, dip, spray or any other method that gives a uniform coating and avoids excessive runs and tears.

Regardless of application method, the dry film thickness of Chemlok 6100 adhesive should be 12.7-25.4 micron (0.5-1.0 mil).

Curing

Chemlok 6100 adhesive cures during the rubber vulcanization process.

Cleanup

Use xylene, toluene or ketones for clean up.

SHELF LIFE/STORAGE

Shelf life is one year from date of shipment when stored at 21-27°C (70-80°F) in original, unopened container. Do not store or use near heat, sparks or open flame.

CAUTIONARY INFORMATION

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Chemlok is a trademark of LORD Corporation or one of its subsidiaries.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.